

PHYSICAL TESTING REPORT



0013

Birchover Stone Ltd
Capstone House
Dunston Way
Off Dunston Road
Chesterfield
S41 9RD

FAO: Mr Nigel Morton

Report of Tests on: Natural Stone Masonry

Your Reference: Birchover Gritstone

Lucideon Reference: (135405)-22969/CR1

Determination of Open Porosity and Apparent Density of Natural Stone

BS EN 1936: 2006

	Open Porosity	Apparent Density
No.	%	kg/m³
1	15.38	2220
2	14.88	2210
3	15.23	2220
4	15.06	2210
5	13.17	2220
6	14.03	2220
Mean	14.63	2220

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

End of Test Report

Mr Simon Hall
Author

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455 Registered Office as above.

Lucideon Ltd
Queens Road, Penkull
Stoke-on-Trent
Staffordshire ST4 7LQ, UK

T +44 (0)1782 764428
enquiries@lucideon.com
www.lucideon.com
Reg. England 1960455